

Solvent-Free Composite PEO-Ceramic Fiber/Mat Electrolytes for Lithium Secondary Cells

Chunsheng Wang,^{a,*,z} Xiang-Wu Zhang,^{b,**} and A. John Appleby^{b,*}

^aCenter for Manufacturing Research and Department of Chemical Engineering, Tennessee Technological University, Cookeville, Tennessee 38505, USA ^bCenter for Electrochemical Systems and Hydrogen Research, Texas Engineering Experiment Station, Texas A&M University, College Station, Texas 77843-3402, USA

Solvent-free composite poly(ethylene oxide) (PEO)-ceramic fiber or mat electrolytes with high ionic conductivity and good interfacial stability have been developed using high-ionic-conductivity $La_{0.55}Li_{0.35}TiO_3$ fibers and mats. The conducting ceramic fibers can penetrate the cross section of the electrolyte film to provide long-range lithium-ion transfer channels, thus producing composite electrolytes with high conductivity. In this work, a maximum room-temperature conductivity of 5.0×10^{-4} S cm⁻¹ was achieved for 20 wt % $La_{0.55}Li_{0.35}TiO_3$ fiber in a PEO-LiN(SO₂CF₂CF₃)₂ mixture containing 12.5 wt % Li⁺ in PEO. The maximum transference number obtained was 0.7. The ceramic fibers in this composite electrolyte are coated by a very thin PEO layer, which is sufficient to provide good interfacial stability with lithium-ion and lithium-metal anodes. © 2004 The Electrochemical Society. [DOI: 10.1149/1.1828952] All rights reserved.

Manuscript submitted May 17, 2004; revised manuscript received June 18, 2004. Available electronically December 6, 2004.

Solvent-free all-solid-state rechargeable lithium secondary cells have been studied extensively in recent years for cellular telephones, laptop computers, electric and hybrid vehicles, and aerospace applications. In a solid-state lithium cell, solid electrolytes serve both as ionic conductor and separator. Therefore, they must meet requirements of high ionic conductivity, high lithium ion transference number, a wide electrochemical stability window, easy processability, and acceptable thermal and mechanical properties. Electrolytes based on poly(ethylene oxide) (PEO) form dimensionally stable films and show high chemical stability to reduction, but have roomtemperature conductivities that are too low $(10^{-7} \text{ to } 10^{-8} \text{ S-cm}^{-1})$ for most applications. Certain ceramics and glasses show much higher Li-ion conductivity. Lithium lanthanum titanate ceramic $(La_{0.55}Li_{0.35}TiO_3)$ has the highest solid-state Li^+ conductivity reported to date ($\sim 10^{-3}$ S-cm⁻¹) at room temperature.¹⁻⁴ Its conductivity of 1.8×10^{-5} S-cm⁻¹ at -50° C is higher than that of typical PEO compositions at 25°C. Unfortunately, La_{0.55}Li_{0.35}TiO₃ ceramic cannot be directly used in lithium secondary cells because it is chemically unstable below 1.5 V vs. Li⁰ due to Ti(IV) to Ti(III) reduction.^{1,3} To enhance the chemical stability of $La_{0.55}Li_{0.35}TiO_3$ at low electrochemical potentials, thin layers of chemically stable PEO-salt complexes or ceramics such as LiPON have been placed between $La_{0.55}Li_{0.35}TiO_3$ plates and lithium metal or lithiated graph-ite anodes.^{4,5} The conductivities of these composite electrolytes can reach 10^{-4} S-cm⁻¹. However, their inflexibility and poor mechanical strength do not allow easy construction of suitable electrochemical secondary cells. Another possible design puts high-conductivity ceramic particles into a PEO-salt complex to form a composite solid polymer electrolyte.⁶ However, poorly conducting interparticle contact results in little improvement in conductivity over that of PEO alone.

The approach suggested here to achieve high ionic conductivity combined with chemical and mechanical stability is the use of $La_{0.55}Li_{0.35}TiO_3$ fibers and/or mats combined with PEO in which an additional very thin PEO layer is coated on the $La_{0.55}Li_{0.35}TiO_3$ surface. A parallel approach, that of filling PEO with nonconducting ceramic (or glass) fibers and mats to reinforce polymer electrolytes, has been reported.⁷⁻⁹ Incorporation of nonconducting ceramic fibers and mats into polymer electrolytes can enhance the mechanical properties of the electrolyte membranes, but decreases the ionic conductivity of the polymer electrolytes. However, $La_{0.55}Li_{0.35}TiO_3$ fiber-PEO electrolytes not only have good mechanical strength but also have high conductivity because the conducting fibers can penetrate the electrolyte film cross section to provide long-range Li^+ transfer channels. The conducting fibers in $La_{0.55}Li_{0.35}TiO_3$ mat-PEO electrolytes have a similar function, but their woven pattern provides better bridging.

Experimental

Electrolyte preparation.-PEO polymer (Aldrich; Mw 600,000 Da) was dried under vacuum at 50°C for 24 h. Lithium bis(perfluoroethylsulfonyl) imide [LiN(SO2CF2CF3)2; 3M Company] and LiClO₄ (Aldrich) were dried at 120°C for 24 h. La_{0.55}Li_{0.35}TiO₃ $(9.1\times 10^{-4}~\text{S-cm}^{-1})$ particles less than 1 μm were prepared from Li₂CO₃, La₂O₃, and TiO₂ starting materials using Inaguma's solidstate reaction method.¹ Stoichiometric amounts of these powders were ground together in an agate mortar and calcined at 800°C for 4 h to eliminate CO₂. The heated powder was ballmilled with ethanol for 1 day, and heated again at 800°C for 2 h. The ballmilled powder was then sieved through a #325 mesh for fiber and mat preparation. La_{0.55}Li_{0.35}TiO₃ powders for filling PEO-LiClO₄ electrolytes were sintered at 1325°C for 2 h. The crystalline phases of La_{0.55}Li_{0.35}TiO₃ powders were identified by X-ray diffraction (XRD) analysis at room temperature using Cu K α radiation. The 2 θ range analyzed was 10-90°, and the scan rate was 2.0° per second. The particle size was observed by scanning electron microscopy (SEM) images using a Jeol JSM-6400 microscope equipped with a Noran 1-2 energydispersive spectrometer. A 15 kV beam was employed generate the backscattered-electron images. Sintered to $La_{0.55}Li_{0.35}TiO_3$ fibers of two different diameters (15 and 250 µm) were produced by Advanced Cerametrics, Inc. using its Viscous Sus-pension Spinning Process (VSSP) method.¹⁰ In the VSSP method, La_{0.55}Li_{0.35}TiO₃ powders were first dispersed in water to give a slurry, which was then mixed with viscose, *i.e.*, cellulose in aqueous sodium hydroxide solution. The mixture was then pumped through spinneret holes into a low-concentration sulfuric acid bath to form particulate La_{0.55}Li_{0.35}TiO₃-loaded cellulose (rayon) fibers. This was followed by sintering at 1325°C for 2 h. To fabricate La_{0.55}Li_{0.35}TiO₃ mats, cellulose fibers loaded with La_{0.55}Li_{0.35}TiO₃ particles were first woven into cloth-like mats, then sintered at 1350°C for 2 h.

 $La_{0.55}Li_{0.35}TiO_3$ fiber-PEO composite electrolytes were prepared from acetonitrile dispersions of weighed quantities of fiber, lithium salt, and PEO to give 12.5 wt % Li⁺ in the PEO matrix. These were ultrasonically vibrated for 8.0 h, cast onto poly(tetrafluoroethylene) films, and dried in air for 24 h, then vacuum dried at 25°C, followed by 80°C, each for 24 h. La_{0.55}Li_{0.35}TiO₃ mat-PEO composite electrolytes were prepared by dropping a fresh solution of PEO and

^{*} Electrochemical Society Active Member.

^{**} Electrochemical Society Student Member.

^z E-mail: cswang@tntech.edu





Figure 3. A spool of green La_{0.55}Li_{0.35}TiO₃ fiber of 15 µm diam.

Results and Discussion

Figure 1. XRD patterns of $La_{0.55}Li_{0.35}TiO_3$ powders calcined at 800°C and sintered at 1325°C.

lithium salt in the same wt % ratio dissolved in acetonitrile into $La_{0.55}Li_{0.35}TiO_3$ mats, followed by rigorous drying as above.

Electrochemical measurements.—The ionic conductivity of the films was measured by electrochemical impedance spectroscopy (EIS) using symmetrical two-electrode cells sandwiching a film between two stainless steel plate electrodes. Spectra were obtained by sweeping from 65 kHz to 1 Hz with a Solartron FRA 1250 frequency analyzer and a Solartron model 1286 electrochemical interface. The high-frequency intercept of the Nyquist plot on the real axis gives the resistance *R* of the electrolyte, from which the ionic conductivity is calculated. Li⁺ transference number (t_{Li+}) measurements were conducted on symmetrical lithium/composite electrolyte/lithium cells by using the method of Bruce and Vincent.¹¹

The stability of the composite electrolyte-lithium electrode interface was investigated by monitoring the time dependence of the impedance of symmetrical Li/composite electrolyte/Li cells under open-circuit conditions. This impedance measurement was obtained by sweeping from 65 kHz to 0.01 Hz using the same equipment as that for the ionic conductivity measurements. Preparation of $La_{2/3-x}Li_{3x}TiO_3$ particles, fibers, and mats.— Figure 1 shows the XRD patterns of $La_{0.55}Li_{0.35}TiO_3$ powders calcined at 800°C and sintered at 1325°C. The powders calcined at 800°C consist only of a mixture of La_2O_3 , Li_2O , and TiO_2 . However, the sintered powders were $La_{0.55}Li_{0.35}TiO_3$, which has a cubic perovskite-type structure. The XRD patterns of the sintered $La_{0.55}Li_{0.35}TiO_3$ powders are in agreement with the previously reported XRD data of a ceramic with a similar composition.¹² $La_{0.55}Li_{0.35}TiO_3$ powder disks were cold-pressed and sintered at 1325°C for 2 h. Their conductivity determined by EIS was *ca*. 9.1 × 10⁻⁴ S-cm⁻¹ at room temperature.

La_{0.55}Li_{0.35}TiO₃ fibers and mats were made from ballmilled La_{0.55}Li_{0.35}TiO₃ particles using the VSSP method. Figure 2 shows SEM images of the ballmilled La_{0.55}Li_{0.35}TiO₃ particles used to prepare fibers and mats. The particle size of La_{0.55}Li_{0.35}TiO₃ was less than 1 μ m after ballmilling for 1 day. Some La_{0.55}Li_{0.35}TiO₃ particles were agglomerated to form large porous particles of 2-3 μ m diam. La_{0.55}Li_{0.35}TiO₃ particles. Figure 3 shows a spool of green La_{0.55}Li_{0.35}TiO₃ fiber of 15 μ m diam, which was woven into a mat (Fig. 4), then sintered at 1325°C for 2 h. Figure 5 shows sintered La_{0.55}Li_{0.35}TiO₃ 15 μ m diam fibers and sintered woven La_{0.55}Li_{0.35}TiO₃ mats.



Figure 2. SEM images of the $La_{0.55}Li_{0.35}TiO_3$ particles prepared by solid-state reaction.



Figure 4. Woven mats made from green $La_{0.55}Li_{0.35}TiO_3$ fibers of 15 μm diam.



Figure 5. Sintered La_{0.55}Li_{0.35}TiO₃ (a) fibers and (b) mats.

Ionic conductivity of fiber-PEO electrolytes.-Perovskite oxides of ABO₃ type such as La_{0.67-r}Li_{3.r}TiO₃ have exceptional ionic conductivity, first reported by Inaguma.¹ However, ceramic membranes formed from these materials are brittle, making them difficult to use in secondary cells. The easiest way to give these materials flexibility is to load particles of ceramic into PEO-salt complexes to form composite polymer electrolytes, which have higher conductivity than the host PEO electrolytes.⁶ In these conducting particle-PEO composite electrolytes, ceramic particles are homogeneously dispersed in the PEO matrix, and hence are separated by relatively thick polymer layers. The poorly conducting contacts between ceramic particles prevent much improvement of conductivity over that of the PEO host. However, conducting ceramic fibers can bridge the gap in the electrolyte film cross section, and hence provide longrange Li⁺ transfer channels. Figure 6 compares the ionic conductivities of electrolytes with 20 wt % La_{0.55}Li_{0.35}TiO₃ particles and 20 wt % La_{0.55}Li_{0.35}TiO₃ 250 µm diam fibers in PEO-LiN(SO₂CF₂CF₃)₂. The fiber-PEO electrolyte has higher conductivity than the particle-PEO electrolyte over the temperature range studied. The roomtemperature conductivity of 20 wt % $La_{0.55}Li_{0.35}TiO_3$ fiber-PEO- $LiN(SO_2CF_2CF_3)_2$ electrolyte was 5.0×10^{-4} S-cm⁻

Figure 7 shows the temperature dependence of ionic conductivity for 50 wt % $La_{0.55}Li_{0.35}TiO_3$ fiber-PEO-LiClO₄ electrolytes with different fiber diameters. Compared to thick fiber-PEO electrolytes, those with thin fibers have a higher area-to-volume ratio in the electrolyte film, giving higher conductivity over the whole temperature range. Fiber diameter therefore plays an important role in determining the ionic conductivity of fiber-PEO composite electrolytes, as does the choice of lithium salt. Figure 8 shows the temperature dependence of ionic conductivity for 250 μ m diam $La_{0.55}Li_{0.35}TiO_3$ fiber-PEO-LiClO₄ and -PEO-LiN(SO₂CF₂CF₃)₂ electrolytes. Because the conductivity of $La_{0.55}Li_{0.35}TiO_3$ fiber is not influenced by the presence of the lithium salt, any changes in electrolyte conductivity must occur in the PEO matrix. LiN(SO₂CF₂CF₃)₂ has large anions which can influence the PEO polymer chain crystallization



 $La_{0.55}Li_{0.35}TiO_3$ particle-PEO-LiN(SO_2CF_2CF_3)_2 and 20 wt % 250 μm

diameter

electrolytes.

La_{0.55}Li_{0.35}TiO₃

fiber-PEO-LiN(SO₂CF₂CF₃)₂

 $\begin{array}{c} 10^{2} \\ (10)^{2} \\ (10)^{3} \\ (10)^{3} \\ (10)^{4} \\ (10)^$

Figure 7. Arrhenius plots for the ionic conductivity of 50 wt % $La_{0.35}Li_{0.35}TiO_3$ fiber-PEO-LiClO₄ composite electrolytes with differing fiber diameters. Thin fiber: 15 µm, thick fiber: 250 µm.

process, promoting amorphous regions with increased ionic conductivity. Therefore, the PEO matrix conductivity still plays an important role in the overall conductivity properties of these composite electrolytes, although the conducting fibers dominate in Li⁺ transfer.

One disadvantage of PEO-based polymer electrolytes is that polymer chain thermal motion can cause the amorphous PEO phase to slowly recrystallize at room temperature, which results in a loss of ionic conductivity during storage. Figure 9 shows the change in the relative conductivity (σ/σ_0) for PEO-LiN(SO₂CF₂CF₃)₂ and 20 wt % La_{0.55}Li_{0.35}TiO₃ fiber (250 µm)-PEO-LiN(SO₂CF₂CF₃)₂ electrolytes over a 35 day period at 25°C. The conductivity of La_{0.55}Li_{0.35}TiO₃ fiber, which penetrates the electrolyte cross section, does not change much during storage. At the same time, the ceramic fibers can also stabilize the conductivity of the PEO matrix by hindering its recrystallization. Therefore, the conductivity loss of La_{0.55}Li_{0.35}TiO₃ fiber-PEO composite electrolyte is less than that of the host polymer electrolyte.

Ionic conductivity and Li^+ transference number of mat-PEO electrolytes.—Fiber-PEO composite electrolytes have a higher conductivity than particle-PEO electrolytes because $La_{0.55}Li_{0.35}TiO_3$ fibers can provide long-range Li^+ transfer channels through the electrolyte film. However, most fibers are parallel to the film plane; hence, only some of the fibers can penetrate the electrolyte completely. Therefore, PEO host conductivity still plays an important role in the overall conductivity of fiber-PEO composite electrolytes, as is shown in Fig. 8. However, when the conducting fibers are woven into mats, they can penetrate the film cross section more readily. Figure 10 compares the ionic conductivies of 50 wt %



Figure 8. Arrhenius plots for the ionic conductivity of 20 wt % $La_{0.55}Li_{0.35}TiO_3$ 250 μ m diam fiber-PEO-LiClO₄ and PEO-LiN(SO₂CF₂CF₃)₂ composite electrolytes.

composite



Figure 9. Relative conductivity (σ/σ_0) vs. time for PEO-LiN(SO₂CF₂CF₃)₂ and 20 wt % 250 μ m diameter La_{0.55}Li_{0.35}TiO₃ fiber-PEO-LiN(SO₂CF₂CF₃)₂ composite electrolytes.

La_{0.55}Li_{0.35}TiO₃ fiber-PEO-LiClO₄ and 70 wt % La_{0.55}Li_{0.35}TiO₃ mat-PEO-LiClO₄ composite electrolytes. Fiber-PEO composite electrolytes with higher than 50 wt % fiber content are easily torn because the fibers are in parallel and the PEO matrix is not strong enough for bonding. The fiber content (70 wt %) of La_{0.55}Li_{0.35}TiO₃ mat-PEO-LiClO₄ electrolytes was obtained by weighing the La_{0.55}Li_{0.35}TiO₃ mat and PEO-LiClO₄ used. From Fig. 10, it is clearly seen that the mat-PEO electrolyte over the whole temperature range studied because of its higher fiber content combined with its regular weave pattern.

The addition of conducting particles only slightly improves the Li⁺ transference number.⁶ However, the Li⁺ transference number of La_{0.55}Li_{0.35}TiO₃ mat-PEO-LiClO₄ composite electrolyte was determined to be about 0.7, much higher than the highest number ($t_{\text{Li+}} = 0.39$) given by La_{0.55}Li_{0.35}TiO₃ particle-filled PEO electrolytes.⁶ The high Li⁺ transference number for the La_{0.55}Li_{0.35}TiO₃ mat-PEO-LiClO₄ composite electrolyte was attributed to the large amount of Li⁺-conducting ($t_{\text{Li+}} = 1.0$) La_{0.55}Li_{0.35}TiO₃ mat in the composite electrolytes.

Interfacial stability with lithium electrode.—La_{0.55}Li_{0.35}TiO₃ ceramic reacts with lithium metal, reducing the tetravalent titanium ions, and producing an electronic or electronic-ionic mixed conductor.¹ As a result, it is very important to prevent the direct contact of ceramic and lithium anodes. In fiber-PEO and mat-PEO composite electrolytes, the conducting ceramic is coated with a very thin PEO-salt layer, which separates the ceramic and lithium electrode. A 20 wt % La_{0.55}Li_{0.35}TiO₃ fiber-PEO-LiN(SO₂CF₂CF₃)₂ was



Figure 10. Arrhenius plots for ionic conductivities of 50 wt % $La_{0.55}Li_{0.35}TiO_3$ fiber-PEO-LiClO₄ and 70 wt % $La_{0.55}Li_{0.35}TiO_3$ mat-PEO-LiClO₄ composite electrolytes.



Figure 11. Interfacial resistances as a function of time for PEO-LiN(SO₂CF₂CF₃)₂ and 20 wt % 250 μ m diam La_{0.55}Li_{0.35}TiO₃ fiber-PEO-LiN(SO₂CF₂CF₃)₂ polymer electrolytes.

sandwiched between two lithium electrodes in a glove box. The color of the sample did not change with time, indicating that no reaction between La_{0.55}Li_{0.35}TiO_3 ceramic and lithium metal occurred, because the color changes from ivory to blue-black on reduction.¹

Any reduction of tetravalent titanium ions starts at the electrolyte-electrode interface. The interfacial resistance between 20 wt % La_{0.55}Li_{0.35}TiO₃ fiber-PEO-LiN(SO₂CF₂CF₃)₂ composite electrolyte and lithium electrode was monitored as a function of time, as shown in Fig. 11. The time dependence of the interfacial resistance for PEO-LiN(SO₂CF₂CF₃)₂ polymer electrolyte is also shown. The interfacial resistance of the latter electrolyte increases markedly at first, then increases irregularly. The initial increase indicates formation of a passivation layer, and the subsequent irregular increase shows that its structure is unstable. The addition of La_{0.55}Li_{0.35}TiO₃ fiber should make the interfacial resistance more unstable if reaction is occurring. However, Fig. 11 shows that La_{0.55}Li_{0.35}TiO₃ fiber stabilizes the interfacial resistance, indicating no interfacial reaction. This interfacial stabilization is attributed to the ability of the La_{0.55}Li_{0.35}TiO₃ fiber surface to scavenge traces of residual impurities in a similar way to added nonconducting ceramic particles.^{13,14}

Conclusions

High-ionic-conducting La_{0.55}Li_{0.35}TiO₃ fibers and mats were successfully prepared using the VSSP method. La_{0.55}Li_{0.35}TiO₃ fibers in fiber-PEO and mat-PEO composite electrolytes can penetrate the electrolyte film, and hence provide long-range Li⁺ transfer channels. La_{0.55}Li_{0.35}TiO₃ mat-PEO composite electrolyte has higher conductivity than fiber-PEO electrolyte because of the woven pattern and higher fiber content. The fiber diameter and the salt type also play an important role in the overall conductivity properties of composite electrolytes.

The reaction between La_{0.55}Li_{0.35}TiO₃ ceramic and lithium anodes is also prevented by the thin PEO-salt layer on the fiber surface. Therefore, these composite electrolytes have good interfacial stability with lithium metal and lithium-ion anodes.

Acknowledgments

We gratefully acknowledge NASA-Glenn Research Center, Cleveland OH, for support of this work under grant no. NAG3-2617.

Tennessee Technological University assisted in meeting the publication costs of this article.

References

- Y. Inaguma, C. Liquan, M. Itoh, T. Nakamura, T. Uchida, H. Ikuta, and M. Wakihara. Solid State Commun. 86 (689 (1993))
- hara, Solid State Commun., 86, 689 (1993).
 A. Varez, M. L. Sanjuan, M. A. Laguna, J. I. Pena, J. Sanz, and G. F. de la Fuente, J. Mater. Chem., 11, 125 (2001).

- C. Wang, P. Patil, A. J. Appleby, F. E. Little, M. Kesmez, and D. L. Cocke, J. Electrochem. Soc., 151, A1196 (2004).
 W. C. West, J. F. Whitacre, and J. R. Lim, J. Power Sources, 126, 134 (2004).
 Y. Kobayashi, H. Miyashiro, T. Takeuchi, H. Shigemura, N. Balakrishnan, M. Tabuchi, H. Kageyama, and T. Iwahori, Solid State Ionics, 152, 137 (2002).
 X. W. Zhang, C. Wang, A. J. Appleby, and F. E. Little, J. Power Sources, 112, 209 (2002).
- (2002).
- C. Yang and S. Lin, J. Power Sources, 112, 497 (2002).
 H. Park, J. Chun, S. Kim, J. Ko, S. Jo, J. Chung, and H. Sohn, J. Power Sources, 92, 272 (2001).
- 9. Z. Wen, M. Wu, T. Itoh, M. Kubo, Z. Lin, and O. Yamamoto, Solid State Ionics, 148, 185 (2002).
- http://www.advancedcerametrics.com/acitechnology.htm
 P. G. Bruce and C. A. Vincent, J. Electroanal. Chem. Interfacial Electrochem., 225,
- 1 (1977).
- J. Ibarra, A. Varez, C. Leon, J. Santamaria, L. M. Torres-Martinez, and J. Sanz, Solid State Ionics, 134, 219 (2000).
- 13. G. B. Appetecchi, F. Croce, L. Persi, F. Ronci, and B. Scrosati, Electrochim. Acta, 45, 1481 (2000).
 14. F. Croce, L. Persi, F. Ronci, and B. Scrosati, *Solid State Ionics*, 135, 47 (2000).